

微波辅助废旧锂电池正极材料有价金属回收技术进展

邱宏菊^{1,2}, 郝先东^{1,2}, 张艳琼^{1,2}, 高磊^{1,2,3}, 陈菓^{1,2,3}

1. 云南民族大学 化学与环境学院, 云南 昆明 650500;
2. 云南省跨境民族地区生物质资源清洁利用国际联合研究中心, 云南 昆明 650500;
3. 非常规冶金教育部重点实验室, 昆明理工大学, 云南 昆明 650093

中图分类号: TD989; TF80; X76 文献标识码: A 文章编号: 1001-0076(2022)03-0038-07
DOI: 10.13779/j.cnki.issn1001-0076.2022.03.006

摘要 在国际前沿和国家战略性关键金属保护的大背景下, 废旧锂电池正极材料中的高价值材料如镍、钴、锰和锂等的回收利用已成为当前的研究热点。论文概述了锂电池正极废弃物有价金属回收工艺, 介绍了微波技术的原理及在冶金过程中的应用, 重点讨论了微波辅助火法—湿法联合工艺在焙烧还原过程、浸出过程、萃取过程的发展态势, 微波的参与节约了碳热还原时间、提高了金属离子的浸出率以及加快萃取过程的传质速率, 最终实现目标金属的产率和品质的提高。最后, 对未来废旧锂电池回收市场的发展前景进行了展望。

关键词 废旧锂电池; 有价金属; 回收工艺; 微波; 锂; 钴

1 引言

锂离子电池作为一种可充电能源, 具有质量轻、自放电低、比能量大、无记忆效应、工作电位高和循环寿命长等特点^[1-2], 在可充电电池中占主导地位。目前, 锂离子电池已普遍应用于便携式电子设备、军事、医疗机械、电动和混合动力汽车以及公共事业服务中^[3-7]。

锂离子电池主要由电池外壳、正极、负极、分隔器微膜、集电器、黏合剂、电解质等部分组成, 大多数锂离子

电池的电池外壳、隔膜、集电器等标准组件基本相同, 主要区别在于正极活性物质(锂化金属氧化物)的类型不同^[8-9]。锂电池各部件的作用和常用材料如表1所示。由表1可以明显看出, 锂电池正极材料中含有许多有价值的金属, 如钴、铝、镍和锂。如果没有得到有效回收, 这些正极金属材料能够与酸、碱、还原剂、强氧化剂产生金属氧化物, 从而产生重金属污染^[10]。因此, 从废锂电池中回收金属不仅可以减少污染物, 还可以增加金属来源, 从而缓解资源紧缺。

表1 锂电池的主要结构及常用材料

Table 1 The main structures and common materials of lithium batteries

电池部件	作用	常用材料
外壳	保护性, 成型	铝壳, 铝塑复合膜, 不锈钢, 聚合物软壳
正极	活性物质	LiCoO ₂ , LiMn ₂ O ₄ , LiNiO ₂ , LiFePO ₄ , LiV ₂ O ₃ , (NiCoMn) ₂ O ₂ , LiNi _x Mn _y Co _z O ₂
负极	活性物质	石墨等碳材料, Li ₄ Ti ₅ O ₁₂ 等非碳材料
集电器	负极或正极的集流体	铜箔(负极), 铝箔(正极)
电解质	传输电极之间的离子	电解质盐: LiPF ₆ , LiBF ₄ , LiClO ₄ , LiSO ₂ , LiCF ₃ SO ₃ , Li(SO ₂ CF ₃); 溶剂: 碳酸丙烯酯(PC), 二甲基亚砜(DMSO), 碳酸乙烯酯(EC)
分隔器微膜	防止电极直接接触造成短路	微孔聚丙烯(PP), 聚乙烯(PE)
黏合剂	黏结和导电	聚偏二氟乙烯(PVDF), 聚四氟乙烯(PTFE)

收稿日期: 2022-04-16

基金项目: 云南省教育厅科学研究基金项目(2022Y459)

作者简介: 邱宏菊(1998-), 女, 四川德阳人, 硕士研究生, 主要从事二次资源综合利用研究, E-mail: 953562963@qq.com。

通信作者: 陈菓(1982-), 男, 重庆人, 博士, 教授, 主要从事冶金工程研究, E-mail: guochen@kust.edu.cn。

在废旧锂电池正极材料有价金属的回收中,微波辅助火法—湿法联合工艺作为一种新兴的技术,实现了低能耗、低污染、多回收种类、高分离纯度的锂电池有价金属的回收^[11-12]。该联合工艺主要由锂电池的前期处理工艺、有价金属浸出工艺以及萃取提纯工艺三部分组成,同时,在每个处理流程中加以微波辅助,可形成环保经济的回收利用体系。总结锂电池正极废弃物中有价金属(Li、Co、Ni、Mn)的回收技术进展,分析各种回收方法的优缺点及微波技术的优势,讨论微波辅助火法—湿法联合工艺在锂电池回收领域的发展态势,可为锂电回收的工业化应用提供参考。

2 锂电池有价金属回收技术现状

近年来,我国锂电池行业正处于前所未有的高速发展期,与此同时,将有一大批锂电池进入规模化退役阶段,锂电池回收市场前景十分广阔^[13]。如果能充分回收镍、钴、锰、锂这些战略性关键金属,将会给社会带来巨大的商业价值^[14]。现如今,针对锂离子电池回收的技术主要有火法冶炼法^[15]、湿法冶炼法^[16]、机械活化法^[17]、生物浸出法^[18]和联合处理技术^[19]。

火法冶炼法是通过废旧锂电池正极材料进行高温煅烧,发生氧化还原反应后形成不混溶的熔融层,冷凝后钴等金属被富集为合金,锂等金属被富集成渣相,从而达到分离金属的目的。湿法冶炼法使浸出溶剂选择性地溶解目的组分,再对目标金属及金属化合物进行分离提纯的一种方法。机械活化法是将正极材料与有机助磨剂混合进行机械球磨化学处理,使其发生物理变化和化学变化,从而实现废旧锂电池正极材料有价金属的分离。生物浸出法是利用微生物辅助正极材料氧化成为可溶性金属硫酸盐,以提高金属浸出率的方法。火法—湿法联合技术主要包括前期处理、浸出以及萃取提纯三大部分,该工艺先对废旧锂电池正极材料进行碳热还原处理,随后利用湿法冶金提炼目标金属。

但是,以上几种技术在应用过程中面临一些技术难题:传统火法焚烧技术由于热传输路径“由外到内”,导致反应时间较长和金属还原不完全,且金属质量损失量随着温度的升高而增加,从而影响活性物质产率比,同时产生的重金属、二噁英等会造成二次污染;湿法冶金技术的药剂使用量大,且容易产生大量高浓度废水,同时锂也分散在这些分离和精炼阶段,导致锂回收率降低;机械活化法对废旧电池内物质的物理属性和化学变化的反应活性要求严格,适用面较窄;生物浸出法对微生物的培养条件要求严格,浸出时间较长。火法—湿法联合技术是目前回收锂电池正极废弃物有价金属的研究热点。此方法实现了高价值金属材料的综合多元化回收,但仍存在成本过高、能耗较大、污染严重的问题。因此,低成本、综合化、多元化、绿色

化的废旧锂电池回收处理技术亟待开发。

3 微波的特点及应用

微波能作为一种清洁能源^[20],被科学工作者们较多地应用于复杂金属氧化物的煅烧还原和浸出萃取等冶金工艺过程^[21-22]。微波辅助冶金过程是利用微波高加热速率^[23]、高选择性^[24]、过程易控制^[25]、节能环保的优势,将其应用于典型的冶金单元过程(还原、煅烧、浸出、萃取等)。其中,微波加热系统的设计很大程度上取决于实际工艺和应用目的,典型的微波加热系统如图1所示。此微波高温管式反应器主要包括了低压部分、高压部分和微波部分,其中微波部分包括了微波高温管式反应器的主要部件微波谐振腔以及一些附属系统等。该微波高温管式反应器主要由以下器件构成^[26]:

(1)微波磁控管,根据实际反应过程的需要,选定磁控管的频率和功率。

(2)微波传输系统,将磁控管产生的微波传输给微波谐振腔,并使得微波在传输过程中功率损耗最低。

(3)微波谐振腔及其附属系统,在微波谐振腔体内实现加热物料与微波能之间的相互作用,从而实现微波加热物料的过程。

(4)多种终端参数测控系统,以测量物料在微波加热过程中的相应参数,如温度、压力等。




图1 典型的微波加热系统^[26]

Fig. 1 Diagram of a typical microwave heating system

现已有研究者对废旧锂离子电池回收过程中金属材料的吸波性能进行全面研究,发现正极金属材料在25~900℃下均具有良好的介电性能,尤其是与炭混合时微波吸收性能更加显著。在金属氧化物的分解和还原过程中,正极的相对介电常数和介电损耗急剧增加,这表明微波加热可以促进还原焙烧过程。当微波功率从1 000 W增加到1 500 W时,材料的加热速率显著提高^[27]。因此,微波辅助火法—湿法联合工艺的研究是未来废锂电池资源可持续回收的发展方向。

4 微波辅助火法—湿法联合工艺

火法—湿法联合工艺主要包括废旧锂电池的前期处理、有价金属的浸出以及浸出液中目标金属的萃取提纯三大重要环节。微波由于其较常规加热空间利用率更高、加热速率更快、产物绿色环保等优势,能在火湿联合工艺的三个重要回收环节中起到强化作用,有助于实现低能耗、低污染、多回收种类、高分离纯度的锂电池有价金属的回收。

4.1 微波辅助废旧锂电池的还原焙烧工艺

废弃锂电池的前处理主要包括深度放电、电池拆解、破碎、物理筛选、各部件组成部分的分离、回收处理电解液等过程^[28];再将分离后的正极材料与还原剂(炭或铝)按比例混合,通过还原焙烧的方法去除电极材料中的有机黏结剂,同时使金属及其化合物发生氧化还原反应,为下一步浸出过程做好准备。


微波加热是从材料内部开始的加热过程,材料内部的介质直接吸收微波能量而引起微波场,由于其高加热空间利用率、选择性加热、高加热速率以及降低金属表观能量的特点,被证明微波碳热还原能对锂电池正极金属材料的回收起到优化作用^[29-30]。Pin 等^[31]将废弃锂离子电池的微波还原和传统的碳热还原回收方法(马弗炉还原)进行比较,两种方法都是在大气环境条件下进行,随后是水浸出和磁选分离,结果发现,与马弗炉还原相比,在同样回收 82% 左右金属锂的情况下,微波使用的还原炭的用量更少;并且微波还原金属锂的耗时更短;以及微波还原导致废旧锂电池正极材料的质量损失更大(见表 2)。

表 2 微波还原和传统的碳热还原的比较^[31]

Table 2 Comparison of microwave reduction and conventional carbon thermal reduction

还原方法	反应条件	反应时间	质量损失	锂的回收率
马弗炉	885 °C, 30% 还原碳	59 min	21.1%	83%
微波	870 W, 24.4% 还原碳	7.8 min	31.6%	82%

Fu 等^[32]提出了一种微波碳热还原和浸出相结合的高效工艺,该工艺是在微波马弗炉(FCG-15 型, 2.45 GHz, 1.6 kW)中,高纯氮气气氛下、以 60 cm³/min 的连续流量进行焙烧试验。此三元锂电池的焙烧还原反应为:



在还原反应后,用盐酸作为浸出液进行浸出,试验结果表明,锂、镍、钴、锰的浸出率比未处理样品的浸出率高,分别高达 99.68%、97.65%、97.85% 和 96.73%。采用阿伦尼乌斯公式计算有价金属在浸出反应中的表

观活化能,得出金属的表观能量降低,这证实了微波还原对后续金属浸出的有效性。微波增强还原反应模型如图 2 所示,可以看出,石墨首先被整体均匀加热。这种加热方法一方面为还原反应提供所需的能量,另一方面热量从颗粒内部均匀地传递到外部,从而避免了阻力。此外,以非均质成分为特征的正极材料不同部位的微波热效应不同,这一结构有利于增加固液接触面积使反应更容易进行。基于以上原理,微波辅助下正极材料中金属的浸出效率得到了提高。







图 2 微波增强还原反应模型示意图^[32]

Fig. 2 Schematic diagram of the microwave - enhanced reduction reaction model

此外,Zhao 等^[33]还研究了微波热解澳洲坚果壳作为炭源,来有效还原回收废旧锂离子电池中的锂。通常,低于 500 °C 时,生物质的微波吸收性较差,但热解后产生的生物炭具有良好的微波吸收能力。此外,具有良好微波吸收性能的废旧锂离子电池正极粉末可以补偿生物质在低温下的较差吸收性能。阴极粉末在微波辐射下会产生高温,使壳粉炭化。这种新形成的澳洲坚果壳生物炭可以在微波辐射下进一步加热混合粉末,并减少金属氧化物。与传统的电阻加热方法相比,通过微波热解获得的生物炭通常具有较大的比表面积和孔隙,这使得生物炭非常适合作为碳热反应的还原剂。用 XRD、SEM 和 TGA 观察了焙烧过程中的相变。在微波加热和生物质热解的作用下,三元材料 $\text{Li}(\text{Ni}_{1/3}\text{Co}_{1/3}\text{Mn}_{1/3})\text{O}_2$ 的初始分解温度降低到 300 °C。在约 680 °C, $\text{Li}(\text{Ni}_{1/3}\text{Co}_{1/3}\text{Mn}_{1/3})\text{O}_2$ 达到条件与生物炭反应并开始剧烈分解(反应 2),系统失重率增加,分解产物继续被生物炭还原见反应式(3) - (6)。



该团队还研究了在生物质用量(Bio 20%)、热解温

度(Pte 500 ℃)、还原焙烧温度(Rte 750 ℃)和还原焙烧时间(Rti 25 min)的条件下,锂的浸出率为93.4%。

综上所述,微波辅助废旧锂电池还原焙烧处理工艺的作用主要体现在:降低焙烧温度,加热速度快,节约碳热还原时间以及增强反应接触面积,从而达到提高有价金属选择性回收的目的。目前,微波加热已经成为一种高效的碳热还原过程强化手段,但是回收过程中炭源(如石墨、生物质)的类型、密度、水分含量和温度对微波吸收性能有很大影响。如何能控制好炭源的使用量,以及增强微波加热的稳定性,实现微波辅助废旧锂电池正极材料还原焙烧处理工艺的全自动化或半自动化,能较大降低能耗,并且符合绿色环保的设计原理。

4.2 微波辅助浸出过程强化工艺

浸出是锂电池回收过程中的关键步骤,其目的是使浸出溶剂选择性地溶解目的组分,得到富含价金属离子的浸出液,以进行目标金属的提取和分离^[34]。浸出方法包括酸浸(无机酸或有机酸)、氨浸、电化学浸出和生物浸出等。酸浸法是正极有价金属回收最常用的方法,常用的无机酸有H₂SO₄、HCl和HNO₃,常用的有机酸有柠檬酸、苹果酸、草酸、琥珀酸和抗坏血酸。两种类型的酸浸法大多数都采用双氧水作为还原剂。

由于微波能将反应提取与高级浸出过程中的快速加热相结合,提高金属溶解率,因而可以使用微波来强化浸出过程。微波作用过程中,极性分子会发生高速振动,增加了物质之间相互碰撞的概率。在固液反应体系中,这种高频振动会使得固体颗粒周围形成局部强烈的液相对流,起到扰动作用,使阻碍反应进行的沉淀物不易沉积在反应颗粒上。这些现象都能够不同程度地强化物质的反应活性,对化学反应起到一定的催化作用^[35],从而极大地缩短浸出时间,节省药剂的用量。为了将常规浸出与微波辅助浸出进行比较,表3总结了不同的操作条件下浸出的指标,通过对比可以得出,在严格控制好微波功率和辐射时间的情况下,能有效提高金属的提取率。

表3 不同操作条件下的正极有价金属回收情况

Table 3 Recovery of valuable metals from positive electrodes under different operating conditions





序号	反应条件	反应时间/min	金属浸出率/%				参考文献
			Li	Co	Mn	Ni	
1	885 ℃, 水浸	60	83	95	70	25	[36]
2	800 ~ 900 ℃, 硫酸	45	88	86	90	-	[37]
3	700 ℃, 柠檬酸	60	80	60	50	83	[38]
4	微波 900 W, 柠檬酸	8	97	93	98	90	[39]
5	微波 900 W, 水浸	8	94	90	98	98	[41]

Patil等^[40]研究了用微波辅助快速溶解法从废旧锂电池中回收锂和钴,并将结果与传统方法(混合酸)进行了比较。在最佳条件下,通过传统方法6 h、80 ℃条件下提取出90%的锂和钴。另一方面,通过微波辅助溶解在180 W、25 min内获得超过85%的锂和钴。因此,25 min的微波辐射产生的溶解量与传统方法中300 min获得的溶解量接近,相应的人力成本也大为降低。因此,微波辅助加热工艺比传统加热工艺更经济,微波辅助溶解法可被认为是从废旧锂电池中回收锂和钴的简单而快速的方法。

Pin等^[41]研究了一种利用微波处理废旧锂电池的短周期循环工艺,发现了正极材料具有良好的微波吸收性能,最佳条件(900 W、8 min)下的磁性部分含钴59.2%、锰15.2%、镍9.07%、氧16.53%。微波照射后,用水浸法将锂提取为纯度95%的碳酸锂。微波处理电极材料显著提高了金属溶出率,锂、钴、锰、镍的提取率分别为94%、90%、98%和98%。

同时,Lie等^[42]还采用抗坏血酸在微波作用下的密闭空间内浸出回收废旧锂电池中的有价金属。抗坏血酸溶液由极性分子组成,极性分子能够很好地吸收微波能量,并在原位进行能量转换产生热量。微波产生的振荡电场诱导极性分子排列,并导致快速加热。偶极分子浓度越高,微波辐射下浸出液中偶极自旋越强烈,促进了快速加热和剧烈的分子碰撞。0.5 mol/L的抗坏血酸在125 ℃下10 min内,以10 g/L的固液比完全浸出锂、钴和锰。显而易见,密闭容器微波系统能显著加速和强化浸出过程,是一种有潜力的从废旧锂电池中高效浸出有价金属的替代技术。

此外,微波还可以与其他强化技术联合优化浸出,Shih等^[43]采用微波和超声波加热联合酸浸、氧化沉淀和溶剂萃取相结合的方法回收和提纯锂电池正极材料中的金属。整个浸出过程涉及的反应方程式有:



为了优化浸出过程,系统地测试了酸和还原剂(H₂O₂)的浓度、固体负载、温度以及微波和超声波加热对钴、锂、锰、镍、铜和铝溶解的影响。其中,微波功率及浸出温度对于浸出溶剂的影响很大,在微波辅助功率475 W、浸出温度90 ℃下,达到最高钴溶解效率(使用柠檬酸为100%,使用琥珀酸为67.8%)所需的时间,较常规浸出显著缩短了30 min。

综上所述,微波处理过程是简单、快速、节能的,在短时间内能极大提高金属离子浸出率。但微波溶解只是早期很快,随着时间的推移会变慢,并且残余浸出剂溶液只能使用常规方法排除。若能进一步改进微波溶

解持久性用于废液的绿色化处理,微波辅助溶解法将更有利于促进废旧锂电池正极材料回收战略的可持续发展。

4.3 微波辅助萃取过程强化工艺

萃取是分离液体混合物过程中的传质操作,应用萃取富集可以有效分离提纯各种有价金属,萃取分离元素的效果可通过萃取剂的种类来控制。其他的提取方法还有离子交换法、电沉积法^[44]。传统萃取法是根据溶质在互不相溶的溶剂里溶解度的不同,利用有机萃取剂将有价金属从浸出液中提取出来的操作方法。但传统的萃取过程萃取剂消耗量大,萃取时间较长。

微波辅助萃取是一种快速的萃取强化技术,其利用高频微波能改变萃取终点的液液相平衡以及加速传热传质过程^[45]。基于极性分子的吸波原理,目标成分的极性越大,微波萃取的效率越高。相比传统萃取法,微波萃取有着减少溶剂用量、缩短加热时间和提高产率等优点^[46],因此微波辅助萃取法有望运用于锂电池有价金属提取工艺中。Grützke 等^[47]将切碎的 $\text{LiNi}_{1/3}\text{Mn}_{1/3}\text{Co}_{1/3}\text{O}_2$ 电池废物悬浮在萃取剂乙腈(CH_3CN)中,在搅拌下使用微波辅助萃取,所得提取物用离子色谱和离子色谱-电喷雾电离-质谱进行分析,确定的金属组分有:锰、铜、钴、镍、锂。Nayl 等^[48]利用钠-二次膦酸萃取剂联合微波萃取强化技术,从混合锂离子电池浸出液中快速萃取分离出锰、钴、镍和锂。在萃取步骤之前,通过在煤油中加入 20% 的 Acorga M5640,在 30 °C 下搅拌 5 min 来除去一些杂质,例如铁(Ⅲ)、铜(Ⅱ)和铝(Ⅲ)。结果表明,采用微波萃取法能极大节约萃取剂的用量,并且通过调节溶液的酸碱度能有效控制金属离子的萃取行为。最终微波辅助下金属离子的萃取率分别为 91.2% Mn(Ⅱ)、89.3% Co(Ⅱ)、95.6% Ni(Ⅱ)、99.1% Li(Ⅰ)。Swain 等^[34]采用无机酸浸法选择性、高效地浸出了钴酸锂正极废料中的有价金属,再从浸出液中使用氰化物 272 萃取剂,运用微波萃取强化技术高效地分离钴和锂。结果表明,在最佳矿浆浓度 2 mol/L、100 g/L 的 H_2SO_4 、5% 的 H_2O_2 、微波处理时间 30 min、温度 75 °C 下,金属离子提取率为 93% Co 和 94% Li。

以上研究表明,微波强化萃取过程的优势体现为试剂用量小,萃取时间短,能有效提高目标成分产率和品质。但在微波的功率和辐射时间、萃取温度和压力的控制上有着严格的要求。总的来说,微波的介入能强化废旧电池中金属离子的萃取,但该工艺还在试验研究阶段,有待工业推广应用,具有极大的发展潜力。

4.4 微波辅助火法-湿法联合工艺发展态势

现阶段,微波辅助火法-湿法联合工艺作为一种低成本、综合化、多元化、绿色化的废旧锂电池回收技

术,是实现锂电池产业可持续绿色发展的有效途径^[49-50]。微波辅助废旧锂电池正极材料有价金属回收技术的优势如下:(1)在还原焙烧工艺阶段,微波加热的热传递方式为从颗粒内部均匀地传递到外部。微波碳热还原具有高加热空间利用率、选择性加热、高加热速率以及降低金属表观能量的特点,能节约还原炭的用量、减少还原金属的时间以及降低污染物的排放。(2)在浸出工艺阶段,微波产生的振荡电场诱导极性分子排列,并导致快速加热。偶极分子浓度越高,微波辐射下浸出液中偶极自旋越强烈,促进了快速加热和剧烈的分子碰撞。这些现象都能够不同程度上强化物质的反应活性,对化学反应起到一定的催化作用,从而极大地缩短了浸出时间,节省了药剂的用量。(3)在萃取工艺阶段,高频微波能改变萃取终点的液液相平衡以及加速传热传质过程。基于极性分子的吸波原理,目标成分的极性越大,微波萃取的效率越高。相比传统萃取法,微波萃取有着减少溶剂用量、缩短加热时间和提高产率等优点。

但微波辅助废旧锂电池正极材料有价金属回收技术也存在一定的局限性:实时加热速率难以控制、易产生局部“热点效应”、吸波物质残留会损害反应器与腔体^[51]。针对以上易出现的问题,研究者可通过对微波辅助火法-湿法联合工艺进行数值仿真模拟来设计精准控制微波系统温度与功率的程序,从而优化微波辅助废旧锂电池正极材料有价金属回收过程的运行条件。此外,还需要对微波处理设备进行研制,以实现半自动或全自动前处理与清洁,最终朝着工业化大规模应用的方向发展。

5 结论

到目前为止,微波技术在废旧锂电池的回收中已取得了显著的研究成果:微波加热的选择性强,加热速度快,是废旧锂电池还原焙烧处理工艺中高效的碳热还原过程强化手段;微波能将反应提取与浸出过程中的快速加热相结合,提高废旧锂电池浸出过程的金属溶出率;高频微波能改变萃取终点的液液相平衡以及加速传热传质过程,有效提高萃取工艺中目标成分的产率和品质。然而,由于锂电池中正极材料的多样性,微波辅助废旧锂电池正极材料有价金属回收技术仍面临着巨大挑战:一方面,需要增强微波加热技术的稳定性,实现前处理工艺的全自动或半自动化;另一方面,要将微波技术与其他强化技术强强联合,开发低能耗、低污染、多回收种类、高分离纯度的回收工艺,以达到国家战略性关键金属全组分、综合化回收的目的。

参考文献:

- [1] ZHENG M, TANG H, LI L, et al. Hierarchically nanostructured transition metal oxides for lithium-ion batteries [J]. *Advanced Science*, 2018, 5(3): 1700592.

- [2] FAN M, CHANG X, MENG Q, et al. Progress in the sustainable recycling of spent lithium-ion batteries[J]. *SusMat*, 2021, 1(2): 241-254.
- [3] LI W, SONG B, MANTHIRAM A. High-voltage positive electrode materials for lithium-ion batteries[J]. *Chemical Society Reviews*, 2017, 46(10): 3006-3059.
- [4] TAO R, XING P, LI H, et al. Recovery of spent LiCoO₂ lithium-ion battery via environmentally friendly pyrolysis and hydrometallurgical leaching[J]. *Resources, Conservation and Recycling*, 2022, 176: 105921.
- [5] SCHMUCH R, WAGNER R, HÖRPEL G, et al. Performance and cost of materials for lithium-based rechargeable automotive batteries[J]. *Nature Energy*, 2018, 3(4): 267-278.
- [6] DUAN X, ZHU W, RUAN Z, et al. Recycling of lithium batteries—a review[J]. *Energies*, 2022, 15(5): 1611.
- [7] YANG Y, OKONKWO E G, HUANG G, et al. On the sustainability of lithium ion battery industry—a review and perspective[J]. *Energy Storage Materials*, 2021, 36: 186-212.
- [8] MAKUZA B, TIAN Q, GUO X, et al. Pyrometallurgical options for recycling spent lithium-ion batteries: a comprehensive review[J]. *Journal of Power Sources*, 2021, 491: 229622.
- [9] CHEN X, GUO C, MA H, et al. Organic reductants based leaching: a sustainable process for the recovery of valuable metals from spent lithium ion batteries[J]. *Waste Management*, 2018, 75: 459-468.
- [10] 王芳,张邦胜,刘贵清,等.废旧动力电池资源再生利用技术进展[J].*中国资源综合利用*,2018,36(10):106-111.
WANG F, ZHANG B S, LIU G Q, et al. Progress in recycling technology of waste power battery resources [J]. *China Resources Comprehensive Utilization*, 2018, 36(10): 106-111.
- [11] MA Y Y, TANG J J, WANALDI R, et al. A promising selective recovery process of valuable metals from spent lithium ion batteries via reduction roasting and ammonia leaching[J]. *Journal of Hazardous Materials*, 2021, 402: 123491.
- [12] ZHANG Y C, WANG W Q, FANG Q, et al. Improved recovery of valuable metals from spent lithium-ion batteries by efficient reduction roasting and facile acid leaching[J]. *Waste Management*, 2020, 102: 847-855.
- [13] 张超,廖青云,路璐,等.锂电池回收产业发展报告[J].*高科技与产业化*,2019(3):36-45.
ZHANG C, LIAO Q Y, LU L, et al. Report on the development of lithium battery recycling industry[J]. *High Technology and Industrialization*, 2019(3): 36-45.
- [14] 靳星,贾美丽,杜浩,等.废旧磷酸铁锂正极材料回收再生研究进展[J].*有色金属工程*,2020,10(11):64-72.
JIN X, JIA M L, DU H, et al. Research progress on recycling of waste lithium iron phosphate cathode materials[J]. *Nonferrous Metal Engineering*, 2020, 10(11): 64-72.
- [15] LIU C, LIN J, CAO H, et al. Recycling of spent lithium-ion batteries in view of lithium recovery: A critical review[J]. *Journal of Cleaner Production*, 2019, 228: 801-813.
- [16] MENG F, LIU Q, KIM R, et al. Selective recovery of valuable metals from industrial waste lithium-ion batteries using citric acid under reductive conditions; leaching optimization and kinetic analysis[J]. *Hydrometallurgy*, 2020, 191: 105160.
- [17] GUAN J, LI Y, GUO Y, et al. Mechanochemical process enhanced cobalt and lithium recycling from wasted lithium-ion batteries[J]. *ACS Sustainable Chemistry & Engineering*, 2017, 5(1): 1026-1032.
- [18] HUANG B, WANG J. Bio-hydrometallurgically treatment of spent Lithium-ion batteries[M]. *Recycling of Spent Lithium-ion Batteries*, 2019: 85-92.
- [19] 李之钦,庄绪宁,宋小龙,等.废锂离子电池正极材料的火法资源化技术研究进展[J].*环境工程*,2021,39(4):115-122.
LI Z Q, ZHUANG X N, SONG S L, et al. Research progress of pyrogenic resource recovery technology for waste lithium-ion battery cathode materials[J]. *Environmental Engineering*, 2021, 39(4): 115-122.
- [20] DIAZ F, WANG Y, MOORTHY T, et al. Degradation mechanism of nickel-cobalt-aluminum (NCA) cathode material from spent lithium-ion batteries in microwave-assisted pyrolysis[J]. *Metals*, 2018, 8(8): 565.
- [21] 庞建明,潘聪超,马永宁,等.微波冶炼低品位锰矿制备含锰生铁的试验研究[J].*中国有色冶金*,2020,49(3):83-87.
PANG J M, PAN C C, MA Y N, et al. Experimental study of microwave smelting of low-grade manganese ore for the preparation of pig iron containing manganese[J]. *China Nonferrous Metallurgy*, 2020, 49(3): 83-87.
- [22] MIZUNO N, KOSAI S, YAMASUE E. Microwave-based extractive metallurgy to obtain pure metals: A review[J]. *Cleaner Engineering and Technology*, 2021, 5: 100306.
- [23] 庞建明,赵沛,郭培民.红土镍矿低温还原+微波冶炼镍铁新技术[J].*中国冶金*,2017,27(9):70-76.
PANG J M, ZHAO P, GUO P M. New technology for low-temperature reduction + microwave smelting of ferronickel from laterite nickel ore [J]. *China Metallurgy*, 2017, 27(9): 70-76.
- [24] FERRARI-JOHN R S, BATCHELOR A R, KATRIB J, et al. Understanding selectivity in radio frequency and microwave sorting of porphyry copper ores [J]. *International Journal of Mineral Processing*, 2016, 155: 64-73.
- [25] MISHRA R R, SHARMA A K. Microwave-material interaction phenomena: heating mechanisms, challenges and opportunities in material processing[J]. *Composites Part A: Applied Science and Manufacturing*, 2016, 81: 78-97.
- [26] 陈蓁.微波法制备人造金红石新工艺及设备研制[D].昆明:昆明理工大学,2012.
CHEN G. New process and equipment development for the preparation of artificial rutile by microwave method[D]. Kunming: Kunming University of Technology, 2012.
- [27] ZHAO Y, LIU B, ZHANG L, et al. Microwave-absorbing properties of cathode material during reduction roasting for spent lithium-ion battery recycling [J]. *Journal of Hazardous Materials*, 2020, 384: 121487.
- [28] 管文字,马北越,刘国强.动力锂电池回收利用现状与展望[J].*稀有金属与硬质合金*,2020,48(5):5-9.
ZAN W Y, MA B Y, LIU G Q. Status and prospects of power lithium battery recycling[J]. *Rare Metals and Cemented Carbides*, 2020, 48(5): 5-9.
- [29] ZHANG J H, GAO L H, HE Z J, et al. Separation and recovery of iron and nickel from low-grade laterite nickel ore by microwave carbothermic reduction roasting[J]. *Journal of Materials Research and Technology*, 2020, 9(6): 12223-12235.
- [30] LI K Q, CHEN J, PENG J H, et al. Pilot-scale study on enhanced carbothermal reduction of low-grade pyrolusite using microwave heating [J]. *Powder Technology*, 2020, 360: 846-854.
- [31] PINDAR S, DHAWAN N. Comparison of microwave and conventional indigenous carbothermal reduction for recycling of discarded lithium-ion batteries[J]. *Transactions of the Indian Institute of Metals*, 2020, 73(8): 2041-2051.
- [32] FU Y P, HE Y Q, YANG Y, et al. Microwave reduction enhanced leaching of valuable metals from spent lithium-ion batteries[J]. *Journal of Alloys and Compounds*, 2020, 832: 154920.
- [33] ZHAO Y Z, LIU B G, ZHANG L B, et al. Microwave pyrolysis of macadamia shells for efficiently recycling lithium from spent lithium-ion batteries[J]. *Journal of Hazardous Materials*, 2020, 396: 122740.
- [34] JIN H, ZHANG J, WANG D, et al. Facile and efficient recovery of lithium from spent LiFePO₄ batteries via air oxidation-water leaching at room temperature[J]. *Green Chemistry*, 2022, 24(1): 152-162.
- [35] DANDIA A, PAREWA V, GUPTA S L, et al. Microwave-assisted Fe₃O₄ nanoparticles catalyzed synthesis of chromeno [1, 6] naphthyridines in aqueous media[J]. *Catalysis Communications*, 2015, 61: 88-91.

- [36] PINDAR S, DHAWAN N. Evaluation of carbothermic processing for mixed discarded lithium – ion batteries [J]. *Metallurgical Research & Technology*, 2020, 117(3): 302.
- [37] PINDAR S, DHAWAN N. Carbothermal reduction of spent mobile phones batteries for the recovery of lithium, cobalt, and manganese values [J]. *JOM*, 2019, 71(12): 4483 – 4491.
- [38] MUSARIRI B, AKDOGAN G, DORFLING C, et al. Evaluating organic acids as alternative leaching reagents for metal recovery from lithium ion batteries [J]. *Minerals Engineering*, 2019, 137: 108 – 117.
- [39] PINDAR S, DHAWAN N. Recycling of mixed discarded lithium – ion batteries via microwave processing route [J]. *Sustainable Materials and Technologies*, 2020, 25: 157.
- [40] PATIL D, CHIKKAMATH S, KENY S, et al. Rapid dissolution and recovery of Li and Co from spent LiCoO₂ using mild organic acids under microwave irradiation [J]. *Journal of Environmental Management*, 2020, 256: 109935.
- [41] PINDAR S, DHAWAN N. Evaluation of in – situ microwave reduction for metal recovery from spent lithium – ion batteries [J]. *Sustainable Materials and Technologies*, 2020, 25: 201.
- [42] LIE J, LIU J C. Closed – vessel microwave leaching of valuable metals from spent lithium – ion batteries (LIBs) using dual – function leaching agent: Ascorbic acid [J]. *Separation and Purification Technology*, 2021, 266: 118458.
- [43] SHIH Y J, CHIEN S K, JHANG S R, et al. Chemical leaching, precipitation and solvent extraction for sequential separation of valuable metals in cathode material of spent lithium ion batteries [J]. *Journal of the Taiwan Institute of Chemical Engineers*, 2019, 100: 151 – 159.
- [44] 王斌, 梁精龙, 李慧, 等. 废旧锂离子电池金属离子回收技术综述 [J]. *电源技术*, 2019, 43(1): 165 – 167.
WANG B, LIANG J L, LI H, et al. A review of metal ion recovery technologies for waste lithium – ion batteries [J]. *Power Technology*, 2019, 43(1): 165 – 167.
- [45] MAO Y, ROBINSON J, BINNER E. Understanding heat and mass transfer processes during microwave – assisted and conventional solvent extraction [J]. *Chemical Engineering Science*, 2021, 233: 116418.
- [46] MARTIN A, NAVARRETE A. Microwave – assisted process intensification techniques [J]. *Current Opinion in Green and Sustainable Chemistry*, 2018, 11: 70 – 75.
- [47] GRÜTZKE M, KRÜGER S, KRAFT V, et al. Investigation of the storage behavior of shredded lithium – ion batteries from electric vehicles for recycling purposes [J]. *Chemistry Sustainability Energy Materials*, 2015, 8(20): 3433 – 3438.
- [48] NAYL A A, HAMED M M, RIZK S E. Selective extraction and separation of metal values from leach liquor of mixed spent Li – ion batteries [J]. *Journal of the Taiwan Institute of Chemical Engineers*, 2015, 55: 119 – 125.
- [49] 李之钦, 李商略, 庄绪宁, 等. 微波焙烧强化废旧锂离子电池中的金属回收研究 [J]. *中国环境科学*, 2021, 41(10): 4712 – 4719.
LI Z Q, LI S L, ZHUANG X N, et al. Study on microwave roasting for enhanced metal recovery from waste lithium – ion batteries [J]. *China Environmental Science*, 2021, 41(10): 4712 – 4719.
- [50] WINDISCH – KERN S, GEROLD E, NIGL T, et al. Recycling chains for lithium – ion batteries: A critical examination of current challenges, opportunities and process dependencies [J]. *Waste Management*, 2022, 138: 125 – 139.
- [51] 孙静, 江镇宇, 于冠群, 等. 微波技术在锂离子电池正极材料高效回收再利用中的研究进展 [J]. *环境工程学报*, 2021, 15(7): 2191 – 2217.
SUN J, JIANG Z Y, YU G Q, et al. Research progress of microwave technology in efficient recycling of lithium – ion battery cathode materials [J]. *Chinese Journal of Environmental Engineering*, 2021, 15(7): 2191 – 2217.

Progress in Microwave – assisted Recovery of Valuable Metals from Spent Lithium Battery Cathode Materials

QIU Hongju^{1,2}, HAO Xiandong^{1,2}, ZHANG Yanqiong^{1,2}, GAO Lei^{1,2,3}, CHEN Guo^{1,2,3}

1. School of Chemistry and Environment, Yunnan Minzu University, Kunming 650500, Yunnan, China;

2. International Joint Research Center for Clean Utilization of Biomass Resources in Cross – border Ethnic Areas, Kunming 650500, Yunnan, China;

3. Key Laboratory of Unconventional Metallurgy, Ministry of Education, Kunming 650093, Yunnan, China

Abstract: Recycling of high – value materials such as Ni, Co, Mn, and Li from used lithium battery cathode materials has become a current research hotspot, resulting from the requirements on the protection of the national strategic key metal and the development of the international frontier. This paper summarized the valuable metals recovery process for waste lithium battery positive electrode, and introduced the principle and application of microwave technology in the metallurgical process. The applications of microwave – assisted heat and humidity combined process in the roasting reduction process, leaching process, and extraction process were studied emphatically. With the involvement of microwave energy, the carbon thermal reduction time was saved, the leaching rate of metal ions was increased and the mass transfer rate of the extraction process was accelerated, ultimately achieving an increase in yield and quality of the target metal. Finally, we prospected the development prospect of waste lithium battery recovery market in the future.

Keywords: waste lithium battery; valuable metals; recycling process; microwave; Li; Co

引用格式: 邱宏菊, 郝先东, 张艳琼, 高磊, 陈菓. 微波辅助废旧锂电池正极材料有价金属回收技术进展 [J]. *矿产保护与利用*, 2022, 42(3): 38 – 44.

QIU Hongju, HAO Xiandong, ZHANG Yanqiong, GAO Lei, CHEN Guo. Progress in microwave – assisted recovery of valuable metals from spent lithium battery cathode materials [J]. *Conservation and Utilization of Mineral Resources*, 2022, 42(3): 38 – 44.